



### SILVER 480 C

Silver 480 C films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow most natural light to pass through. Solar glare is greatly diminished and its one-way mirror aspect guarantees privacy from prying eyes, whilst affording a modern feel to the exterior of a building. A highly resilient film, it helps to secure your windows by ensuring that the glass does not shatter in the event of an impact or explosion. Conforms to European Standard EN 12600.



SOLAR SCREEN® Warranty

10 YEARS



Fire-resistance rating





Storage from -5°C to +40°C





European Standard EN 12600 **2B2** 



REACH RoHS compliant

RESPECTED

## WIDTHS AVAILABLE:

122 cm

152 cm

### TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	18 %
Reflection of external visible light	60 %
Reflection of internal visible light	58 %
Total solar energy rejected	80 %
Total solar energy rejected 2*	75 %
Solar ratio:	
Solar energy reflection	56 %
Solar energy absorption	33 %
Solar energy transmission	11 %
Reduction in Solar Glare	83 %
g-value	0.20
u-value	5.1
Shading coefficient	0.2
Tensile strength (kg/cm <sup>2</sup> )	28
Elongation at break	125%
Installation type: Interior	
Roll length	30,5 m
Film composition	PET
Thickness	125 μ
Colour from the outside: SILVER	

recommended

glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.

### INSTALLATION ADVICE


Vertical installation and on standard glass surface\*\*

Clear single pane	<b>~</b>
Tinted single pane	<b>~</b>
Reflective tinted single pane	<b>V</b>
Clear double pane	<b>V</b>
Tinted double pane	×
Reflective tinted double pane	<b>~</b>
Gas-filled double pane - Low E	1
STADIP EXT. clear double pane	1
STADIP INT. clear double pane	×

\*Recommendations provided on the basis of a

# **CONSTRUCTION**

- 1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
- 2. High optical quality polyester, with anti IR metal particles
- deposit
  3. Bonding adhesive
  4. High optical quality polyester
- 5. Reinforced PS Adhesive to accompany the elasticity of the film in case of impact, glass polymerization within 30 days
- **6.** Protection release liner, disposable after installation



# **MAINTENANCE INSTRUCTIONS**

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time. Consult our guarantee vouchers and our general conditions of sale.